

Concentrated Stabilizer

KEIHIN-IIIC


1. Features

KEIHIN-IIIC is stable in long term

KEIHIN-IIIC retains more than 48hrs retardation under the Singapore weather condition.

Specific Mix (Example)

Backfill Grout A Liquid (920L)	
Cement	250kg
Bentonite	30kg
KEIHIN-IIIC	2.5L
Water	824L



KEIHIN-IIIC has minimum influence to the environment

KEIHIN-IIIC consists of mainly dextrose which is used as food additive.

Therefore influence to the environment is insignificant / (minimal impact)

2. Properties

Appearance	Dark Brown Liquid
Specific Gravity	1.20 ~ 1.23
Viscosity	Less than 100pas
PH	6±1

3. Packing Condition

1,200kg Container (1m3)

Keihin Soil Co., Ltd.

Post Code 232-0023 Shirotae-Cho 5-59 Minami-ku

Yokohama City Kanagawa Prefecture, Japan

Tel +81-45-231-4856 Fax +81-45-231-4081